







## The entire range at a glance

Exolon® multi UV  
Polycarbonate Multiwall Sheets

Geometry	Type	Sheet Thickness A	Rib-distance B	Ug-value (vertical) (EN-ISO-10077-2) (W/m²K)	Light transmission TD65 (%)	
					clear 1099	white 1146
	Exolon Multi UV 2/4-8	4	8	4	84	77
	Exolon Multi UV 2/6-8	6	8	3,5	82	77
	Exolon® Multi UV 2/8-10,5	8	10,5	3,3	81	78
	Exolon® Multi UV 2/10-10,5	10	10,5	3	80	70
	Exolon® Multi UV 2/16-30	16	30	2,8	77	57
	Exolon® Multi UV 3/16-20	16	20	2,2	74	62
	Exolon® Multi UV 4/10-6	10	6	2,5	68	61
	Exolon® Multi UV 7/16-14	16	14	1,8	55	45
	Exolon® Multi UV 7/20-14	20	14	1,5	55	44
	Exolon® Multi UV 7/25-14	25	14	1,4	54	42
	Exolon® Multi UV 5X/8-25	8	25	2,8	71	63
	Exolon® Multi UV 5X/10-25	10	25	2,5	68	61
	Exolon® Multi UV 5X/16-25	16	25	2	64	55
	Exolon® Multi UV 5X/20-25	20	25	1,9	60	51
	Exolon® Multi UV HX/25-32	25	32	1,3	46	38
	Exolon Multi UV HX/32-32	32	32	1,1	45	36
	Exolon Multi UV HX/40-32	40	32	1	44	34
	Exolon Multi UV HX/50-32	50	32	0,85	46	31

For more details please check our technical documentation.

Covestro also produces solid sheets in polycarbonate (Exolon® GP) and in polyester (Vivak® and Axpel®).  
For more information, take a look at [www.sheets.covestro.com](http://www.sheets.covestro.com).



Exolon Group S.p.A  
Strada Di Vagno 15/A –  
05035 Nera Montoro (TR)  
Italy

[sales@exolongroup.com](mailto:sales@exolongroup.com)  
[www.exolongroup.com](http://www.exolongroup.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. Exolon® is a registered trademark by Exolon Group.