

Tip, April 2020

Cleaning Tip for Makrolon[®], Vivak[®] and Axp[®]

General Cleaning Instructions

Makrolon[®], Vivak[®] and Axp[®] sheet can be cleaned by washing with lukewarm water containing a mild soap or a slightly acidic, neutral or slightly alkaline detergent using a soft clean sponge. Rinse well afterwards with clean water and dry with a chamois or a moist cellulose sponge.

Fresh paint splashes, grease, smeared glazing compounds, fingerprints, etc. can be removed before drying with a soft cloth and ethanol, 2-propanol or isopropanol or petroleum ether (ingredients are listed on most products) by gently rubbing and then washing and rinsing thoroughly as described above.

For disinfection we recommend to use products based on the ingredients: Ethanol or 2-propanol or hydrogen peroxide. Other substances can attack the surface of the board. If you do not know the ingredients, please carry out a test on one corner of the board to ensure that it does not attack the surface or leave a residue. It is recommended to clean the sheets with clean water

Please avoid:

Do not use abrasive or strongly alkaline cleaning agents such as ammonia. Furthermore, we recommend not to use products containing e.g. acetone, MEK, methanol, methylene chloride, carbon tetrachloride or other solvents and to refrain from using petrol, nail polish remover or paint stripper.

Never scrape with razor blades or other sharp objects.

Exolon Group GmbH
Rommerskirchener Str. 21
50259 Pulheim
Germany

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon[®] is a registered trademark, owned and licensed by Covestro Group

Vivak[®] und Axp[®] sin are a registered trademarks of Exolon Group

The logos for Makrolon, Vivak, and Axp. Makrolon is in red, Vivak is in blue, and Axp is in light blue. Each logo has a registered trademark symbol (®) to its upper right.

MF1166 UK