

Product data sheet, April 2021

Exolon[®] multi UV 5M/32-20 Multiwall polycarbonate sheet



Your benefits:

- extremely heat-insulating
- high rigidity
- good load bearing capacity

Exolon® multi UV 5M/32-20 is a polycarbonate sheet of 32 mm thickness, with a M-structure for enhanced stiffness. It combines good load bearing properties, excellent thermal insulation, light transmission and excellent weather resistance. The sheet is lightweight, impact resistant and easy to install.

Exolon® multi UV 5M/32-20 is ideal for flat glazing applications.

- conservatories
- industrial glazing, sports halls
- partition walls
- skylights, northlight glazing
- roofing, cladding (facades)

The sheets are produced with a coextruded UV-protective layer, which is homogeneously fused with the sheet material. This UV-protected side must be installed facing upwards/outwards. It provides **Exolon® multi UV** with a highly effective protection against weathering, guaranteed for 10 years.

On request:

IQ-Relax

Exolon® multi IQ-Relax are opal white sheets, which dramatically reduce the heat of the sunlight, allowing the visible light to pass through. More light, less heat!




TECHNICAL DATA (TYPICAL VALUES)

| Area weight | 3.7 kg/m² | 3.7 kg/m² | | | |
|---|---|--|--|--|--|
| Sheet width | 980, 1,200, 1,230 | 980, 1,200, 1,230, 2,100 mm | | | |
| Possible delivery lengths | 2,000 to 6000 mr | 2,000 to 6000 mm | | | |
| Light transmittance τ _{D65} UV-absorbing) | clear 1099: white 1146: IQ-Relax: bronze 1845: | approx. 48 % approx. 38 % approx. 30 % approx. 12 % | | | |
| Total energy transmission g | clear 1099: white 1146: IQ-Relax: bronze 1845: | approx. 47 % approx. 41 % approx. 32 % approx. 31 % | | | |
| Heat transfer coefficient Ug (2) | 1.2 W/m² K | 1.2 W/m² K | | | |
| Coefficient of thermal expansion $lpha$ | 0.065 mm/m °C | 0.065 mm/m °C | | | |
| Possible expansion due to heat and moisture | 3 mm/m | | | | |
| Max. service temperature without load | 120°C | 120°C | | | |
| Fire rating (1) • Europe all colours | B-s1, d0 (EN1350 | B-s1, d0 (EN13501-1) | | | |

⁽¹⁾ Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.

⁽²⁾ Heat transfer coefficient Ug according to EN ISO 10077-2







Exolon[®] multi UV 5M/32-20 Multiwall polycarbonate sheet

Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.


When using **Exolon® multi UV 5M/32-20** in roof or wall installations, the forces exerted by snow and wind loads must be absorbed by a suitable substructure. We recommend implementing the support distance indicated in the diagram for the respective loads.

The diagram shows the load-bearing capacity of **Exolon® multi UV 5M/32-20** (supported on all sides, rebate depth \ge 20 mm) with a standard profile on the longitudinal sides. The load-bearing curves enable the user to calculate the actual load-bearing characteristics of the multi-wall sheets in their support construction.

If the rebate depth is smaller, the support distances should be reduced in accordance with the relevant load. For wind forces alone, the loads are permitted to be multiplied by 1.1.

Load bearing characteristics (determination)*:


The component resistance (limit state of load bearing capacity) of **Exolon® multi UV 5M/32-20** has been calculated by using test reports on similar products. These values are reference values, adequate safety margins must be observed in addition to these values. The margins are to be assessed on a case-by case-basis.



In general, experience has proven that a safety factor of 1.3 is adequate with regard to the measured resistance values. This safety factor is included in the load tables and diagram.

These specifications do not replace national regulations, such as building inspectorate approval in Germany (DIBt), Avis Techniques in France, etc.

*Further information can be obtained on request



| Load | kN/m² | 0.75 | 1.0 | 1.25 | 1.5 | 2.0 | Width in mm |
|-------------------|-------|------|-----|------|-----|-----|-------------|
| Length or support | m | œ | 5.4 | 4.4 | 3.9 | 3.1 | 980 |
| spacing A | m | 5.8 | 4.7 | 4.0 | 3.4 | 2.7 | 1,200 |
| | m | 2.2 | 1.8 | 1.5 | 1.3 | 1.1 | 2,100 |

Exolon Group also produces solid sheets in polycarbonate (Exolon® GP) and in polyester (Vivak® and Axpet®). For more information, take a look at www.exolongroup.com.



Exolon Group S.p.A Strada Di Vagno 15/A – 05035 Nera Montoro (TR)

Italy

www.exolongroup.com sales@exolongroup.com The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance, and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Evolon Group. Unless we otherwise agree in writing, all products are solid strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and agreed that you assume and hereby expressly release us from all liability, in or use any products, incordial assistance, and information. Any statement or recommendation not contained herein is sultability form a hall not bind. Nothing herein is hall be construed as a recommendation to use any products are solid to use any products are solid as well as health, we and hereby existence, and information. Any statement or recommendation not contained herein is usual but on thorized and shall not bind. Nothing herein is hall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Exolon® is a registered trademark of Exolon Group