

# Exolon® Silent Sound UV/AR

## Solid polycarbonate sheet 18 mm



### Your benefits:

- Tested safety according to ZTV-LSW06/EN 14388
- Noise reduction  $DL_r$ : 34 dB
- 18 mm sheet thickness with extended UV protection
- Good fire rating

Solid **Exolon® Silent Sound** sheets are clear, polished, UV-stabilized polycarbonate sheets and available as extended UV and Abrasion-resistant version. They offer extreme impact strength that exceeds the physical properties of other products of their class. Exolon® sheets resist temperatures of -100 to +120 °C, exhibit high optical clarity and have a good fire rating.

**Exolon® Silent Sound** sheets meet the sound technical requirements for noise reduction and the demands of road safety, stability such as form and ageing stability.

**Exolon® Silent Sound UV** can be bent cold and also manufactured flat.

### Applications:

**Exolon® Silent Sound** can be used for noise protection barriers on motorways with heavy traffic, dual carriageways and railways.

The sheets offer protection against involuntary breakage and willful destruction. **Exolon® Silent Sound** sheets can be thermoformed, cold-curved and machined with ease.

	Test Conditions	Typical values <sup>(1)</sup>	Unit	Standard
<b>PHYSICAL</b>				
Density		1200	kg/m <sup>3</sup>	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	-	ISO 489
<b>MECHANICAL</b>				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Nominal strain at break	50 mm/min	> 50	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m <sup>2</sup>	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm	80P	kJ/m <sup>2</sup>	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	70P	kJ/m <sup>2</sup>	ISO 180-A
<b>THERMAL</b>				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	104/K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2
<b>ELECTRICAL</b>				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	-	IEC 60250
Relative permittivity	1 MHz	3.0	-	IEC 60250
Dissipation factor	100 Hz	5	10 <sup>-4</sup>	IEC 60250
Dissipation factor	1 MHz	95	10 <sup>-4</sup>	IEC 60250


<sup>(1)</sup> These values are measured on injection molded samples, and are not intended for specification purposes.

# Exolon® Silent Sound UV/AR

## Solid polycarbonate sheet 18 mm



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.



RESULTS dB [EN ISO 140-3]		
Sum of deviation	26.8	
Average deviation	1.79	
Displacement designated curve	-15	
Sound reduction index $R_w$	37	
Spectrum adaptation terms		
	C	$C_{tr}$
100 – 3,150 Hz	-2	-3
100 – 5,000 Hz	-1	-3
50 – 3,150 Hz	-2	-4
50 – 5,000 Hz	-1	-4
$\Delta L_{A,R,St}$ (ZTV-LSW 88)	34	
$DL_R$ (DIN EN 1793-2)	34 (B3)	

EUROPEAN CERTIFICATES for Exolon® Silent Sound UV	
<b>Resistance to brushwood fire according to (*):</b>	
DIN EN 1794-2, Annex A: Class 2 ZTV-LSW 06, Section 2.5.4	
<b>Impact of Stones according to:</b>	
DIN EN 1794-1, Annex C: Passed	
<b>Danger of falling debris according to:</b>	
DIN EN 1794-2, Annex B: Class 6	

(\*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.



Exolon Group NV  
Wakkensesteenweg 47  
8700 Tielt

Belgium

www.exolongroup.com  
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group