

Exolon® DX Line

Solid polycarbonate sheet for LED lighting



Your benefits:

- extreme high light transmission and high diffusivity at the same time
- extreme impact strength
- resistance to wide range of temperature

Solid **Exolon® DX** sheets are polished polycarbonate diffuser sheets. **Exolon® DX** is developed for applications based on LED light sources, which do not emit UV light. It offers a combination of high light transmission and light diffusion as well as an extreme impact strength which exceeds the physical properties of other thermoplastics. Exolon® sheets resist temperatures of -100 to +120 °C.

Exolon® DX Cool is a diffuser sheet with a cool and fresh color appearance, even when the LEDs are in off mode.

Exolon® DX Bright is an opal white, translucent solid diffuser sheet with a matte and a glossy surface.

Exolon® DX High is an opal white, translucent solid sheet with a matte and bright surface. Special diffusion material ensures lower light diffusion than in the DX Bright.

Exolon® DX-NR and **Exolon® DX-UV** are the perfect choice for a long service life because of their good weathering performance, backed up by a 10-year warranty. **Attention:** the sheet must be mounted with the UV protection layer facing the sun.

Applications:

Typical applications for **Exolon® DX** diffuser sheets include all kinds of LED lighting fixtures and luminaires. The sheets offer protection against involuntary breakage and willful destruction therefore can also be applied in LED-based signage applications and street furniture where efficient lighting technologies are in use. **Exolon® DX** sheets can be thermoformed, cold-curved and fabricated with ease.

	Test Conditions	Typical Values ⁽¹⁾	Unit	Test Method
PHYSICAL				
Density		1200	kg/m ³	ISO 1183-1
Water absorption saturation	water at 23°C	0.3	%	ISO 62
Water absorption equilibrium	23°C, 50% RH	0.12	%	ISO 62
Refractive Index	Procedure A	1,586	-	ISO 489
MECHANICAL				
Tensile modulus	1 mm/min	2300	MPa	ISO 527-1,-2
Yield stress	50 mm/min	>60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Strain at break	50 mm/min	120	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2300	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23°C, unnotched	non-break	kJ/m ²	ISO 179-1eU
Charpy impact strength	23°C, 3 mm, notched	70P	kJ/m ²	ISO 179-1eU
Izod impact strength	23°C, 3.2 mm, notched	80P	kJ/m ²	ISO 180-A
THERMAL				
Vicat softening temperature	50 N; 50°C/h	144	°C	ISO 306
Thermal conductivity	23°C	0.2	W/(mK)	ISO 8302
Coefficient of thermal expansion	23 to 55°C	0.65	10 ⁻⁴ K	ISO 11359-1,-2
Temperature of deflection under load	1.8 Mpa	126	°C	ISO 75-1,-2
	0.45 Mpa	138	°C	ISO 75-1,-2
ELECTRICAL				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	-	IEC 60250
Relative permittivity	1 MHz	3	-	IEC 60250
Dissipation factor	100 Hz	5 · 10 ⁻⁴	-	IEC 60250
Dissipation factor	1 MHz	90 · 10 ⁻⁴	-	IEC 60250

⁽¹⁾ These values are measured on injection molded samples, and are not intended for specification purposes.

Exolon® DX Line

Solid polycarbonate sheet for LED lighting



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Light Transmission:

Test Method according to CIE 130-1998, on a spherical photometer with a diameter of 1.5 m. Please ask us for more information. The stated values are typical values only.

	DX Cool		DX Bright		DX High	
Sample Thickness [mm]	1,5	3,0	1,5	3,0	1,5	3,0
τ_{D65}	65%	64%	74%	76%	84%	84%

Light diffusion:

According to DIN 5036-3 with a swivel-arm device using a luminance meter of class L (Fa. LMT) and a illuminance meter of class A (Fa. Czibula & Grundmann GmbH).

	DX Cool		DX Bright		DX High	
Sample Thickness [mm]	1,5	3,0	1,5	3,0	1,5	3,0
Half power angle [γ]	76°	75°	49°	40°	21.5°	20°
Light diffusion factor [σ]	79%	77%	60%	53%	34%	30%

Dimensions:

Thicknesses: **Exolon® DX** line will be available in 1.5 mm and 3.0 mm

Sizes: **Exolon® DX** line will be available in 2,050 x 1,250 mm

Upon request and quantity requirements, other dimensions can be offered.

Permanent Service Temperature:

The permanent service temperature without load is approx. 120 °C.

Fire Rating*:

Country	Standard	Rating	Thickness	Colour
Europe	EN 13501-1	B-s1-d0	1.5/ 5.0 mm	DX Cool/Bright/High
UK	BS 476-7	Class 1Y	1.5/ 5.0 mm	DX Cool
USA	UL 94	V2	1.5 mm	DX Cool/Bright/High
		V2	2.0 mm	DX Cool/Bright/High
		HB	3.0 mm	DX Cool/Bright/High

* Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered product in accordance with the indicated fire classification standards.

Glow Wire Flammability Tests:

Glow Wire Flammability Index (GWFI): 1.5/3.0 mm: 850°C

Glow Wire Ignition Test (GWIT): 1.5/3.0 mm: 875°C



Exolon Group NV
Wakkensesteenweg 47
8700 Tielt

Belgium

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group