

Makrolon® RX-Line

Solid polycarbonate sheet for LED lighting



I Line
Innovative

Your benefits:

- extreme high light reflection and high opacity at the same time
- excellent fire properties
- extreme impact strength
- resistance to wide range of temperature

Solid **Makrolon® RX** sheets are highly reflective opaque solid polycarbonate sheets. **Makrolon® RX** is developed for applications based on LED light sources, which do not emit UV light. It offers a combination of Lambertian light reflectance of incident light with the opacity and exhibits excellent fire behavior and high impact strength. Makrolon® sheets resist temperatures of -100 to +120 °C. **Makrolon® RX** sheets can be thermoformed, cut, punched or otherwise fabricated with ease.

Makrolon® RX is an ultra-white opaque sheet offering a combination of high light reflectance in the LED spectral range together with its very high opacity.

Makrolon® RX-FR is a white opaque sheet offering high light reflection in the LED spectral range and exhibits silk-matt surface which aids the diffuse reflectance of the incident light. Highly flame-retarding **Makrolon® RX-FR** comes with a UL listed flammability rating.

Applications:

Typical applications for **Makrolon® RX** sheets are LED light fittings and fixtures, e.g.:

- flat and thermoformed reflectors,
- components of lamp interiors,
- external (housing) parts,
- indirect lighting
- back reflectors in edge-lit panels.

	Test Conditions	Makrolon RX ⁽¹⁾	Makrolon RX-FR ⁽²⁾	Unit	Test Method
PHYSICAL Density Water absorption saturation Water absorption equilibrium	water at 23°C 23°C, 50 % relative humidity	1340 0.30 0.12	1340 0.30 0.12	kg/m ³ % %	ISO 1183-1 ISO 62 ISO 62
MECHANICAL Tensile modulus Nominal strain at break Charpy impact strength	1 mm/min 50 mm/min 23°C, unnotched	2700 50 non-break	2700 50 non-break	MPa % kJ/m ²	ISO 527-1,-2 ISO 527-1,-2 ISO 179-1eU
THERMAL Vicat softening temperature Coefficient of thermal expansion	50 N; 50°C/h 23 to 55°C	140 0.65	140 0.65	°C 10 ⁻⁴ K	ISO 306 ISO 11359-1,-2
ELECTRICAL Electrical strength Volume resistivity Surface resistivity Relative permittivity Relative permittivity Dissipation factor Dissipation factor	1 mm 100 Hz 1 MHz 100 Hz 1 MHz	31 8.2 E14 1 E17 3.5 3.4 8 97	34 6 E14 5.3 E16 3.5 3.4 8 93	kV/mm Ohm.m Ohm - - 10 ⁻⁴ 10 ⁻⁴	IEC 60243-1 IEC 60093 IEC 60093 IEC 60250 IEC 60250 IEC 60250 IEC 60250

⁽¹⁾ RX sheet thickness 1/ 2/ 3/ 4 mm (other thickness on request)

⁽²⁾ RX FR sheet thickness 1,5/ 2/ 3/ 4 mm (other thickness on request)

Makrolon® RX-Line

Solid polycarbonate sheet for LED lighting



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Optical Properties:

Test Method according to DIN EN ISO 13468-2

Makrolon® Type	RX	RX-matte	RX-UV	RX-FR
Light reflectance D65	> 96%	94%	95%	> 94%
YI D65	< 2	< 3	< 3	< 4
gloss60° (ISO 2813)	< 110	< 3	110	< 30

Dimensions:

Thicknesses: **Makrolon® RX** line is available in 1.0 mm. Other thicknesses on request.

RX-FR and **RX matte** are available only on request.

Sizes: **Makrolon® RX** line is available in 1.250 x 2.050 mm

Upon request and quantity requirements, other dimensions can be offered

Permanent Service Temperature:

The permanent service temperature without load is approx. 120 °C.

Fire Rating (*):

	Makrolon® RX		Makrolon® RX-FR		Makrolon® RX matte
Sample thickness (mm)	1.5	3.0	1.5	3.0	1.0
UL 94	V-2**	V-2**	V-0	V-0	V-2**

*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.

**) Only indicative test result, no Yellow Card.

Glow Wire Flammability Tests:

Test method according to IEC 60695-2-12

Glow Wire Flammability Index (GWFI):	Makrolon® RX	1 mm:	850°C
	Makrolon® RX,	1.5/3.0 mm:	960°C
	Makrolon® RX-FR,	1.5/3.0 mm:	960°C

Glow Wire Ignition Test (GWIT):	Makrolon® RX	1 mm	850°C
	Makrolon® RX,	1.5 mm:	825°C
	Makrolon® RX,	3.0 mm:	850°C
	Makrolon® RX-FR,	1.5/3.0 mm:	850°C



Exolon Group GmbH
Rommerskirchener Str. 21
50259 Pulheim
Germany

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group