

Product data sheet, May 2021

Exolon® RX-Line Solid polycarbonate sheet for LED lighting



Your benefits:

- extreme high light reflection and high opacity at the same time
- excellent fire properties
- extreme impact strength
- resistance to wide range of temperature

Solid **Exolon® RX** sheets are highly reflective opaque solid polycarbonate sheets. **Exolon® RX** is developed for applications based on LED light sources, which do not emit UV light. It offers a combination of Lambertian light reflectance of incident light with the opacity and exhibits excellent fire behavior and high impact strength.Exolon® sheets resist temperatures of -100 to +120 °C. **Exolon® RX** sheets can be thermoformed, cut, punched or otherwise fabricated with ease.

Exolon® RX is an ultra-white opaque sheet offering a combination of high light reflectance in the LED spectral range together with its very high opacity.

Applications:

Typical applications for **Exolon® RX** sheets are LED light fittings and fixtures, e.g.:

- flat and thermoformed reflectors,
- components of lamp interiors,
- external (housing) parts,
- indirect lighting
- back reflectors in edge-lit panels.

| | Test Conditions | Exolon RX ^(*) | Unit | Test Method | |
|--|--|---|--|--|--|
| PHYSICAL Density Water absorption saturation Water absorption equilibrium | water at 23°C 23°C, 50 % relative humidity | 1340 0.30 0.12 | kg/m³ % % | ISO 1183-1 ISO 62 ISO 62 | |
| MECHANICAL Tensile modulus Nominal strain at break Charpy impact strength | 1 mm/min 50 mm/min 23°C, unnotched | 2700 50 non-break | MPa % kJ/m² | ISO 527-1,-2 ISO 527-1,-2 ISO 179-1eU | |
| THERMAL Vicat softening temperature Coefficient of thermal expension | 50 N; 50°C/h 23 to 55°C | 140 0.65 | °C 10 ⁻⁴ K | ISO 306 ISO 11359-1,-2 | |
| ELECTRICAL Electrical strength Volume resistivity Surface resistivity Relative permittivity Relative permittivity Dissipation factor Dissipation factor | 1 mm 100 Hz 1 MHz 100 Hz 1 MHz | 31 8.2 E14 1 E17 3.5 3.4 8 97 | kV/mm Ohm.m - - 10 ⁻⁴ 10 ⁻⁴ | IEC 60243-1 IEC 60093 IEC 60093 IEC 60250 IEC 60250 IEC 60250 IEC 60250 IEC 60250 | |

(*) RX sheet thickness 1 mm



Exolon® RX-Line Solid polycarbonate sheet for LED lighting



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Optical Properties:

Test Method according to DIN 5036.

| Exolon [®] -Type | RX |
|---------------------------|--------|
| Light reflectance D65 | > 96 % |
| YI D65 | < 2 |
| gloss60° (ISO 2813) | < 110 |

Dimensions:

 Thicknesses:
 Exolon® RX line is available in 1.0 mm.

 Sizes:
 Exolon® RX line is available in 1.250 x 2.050 mm

 Upon request and quantity requirements, other dimensions can be offered

Permanent Service Temperature:

The permanent service temperature without load is approx. 120 °C.

Fire Rating (*):

| Exolon [®] RX | |
|------------------------|--|
| 1,0 | |
| V-2** | |
| | |

*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards. **) Only indicative test result, no Yellow Card.

Glow Wire Flammability Tests:

Test method according to IEC 60695-2-12

| Glow Wire Flammability Index (GWFI): | Exolon® RX | 1 mm: | 850°C |
|--------------------------------------|------------|-------|-------|
| Glow Wire Ignition Test (GWIT): | Exolon® RX | 1 mm | 850°C |



Exolon Group NV Wakkensesteenweg 47 8700 Tielt

Belgium

www.exolongroup.com sales@exolongroup.com The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance, and information are suitable for your intended uses and applications. This applications - specific analysis must at least include testing to determine suitability from a technical assistance, and information or are suitable for your intended uses and applications. This applications - specific analysis must at least include testing to determine suitability from a verila sheath, afety, and environmental standpoint. Such testing has not necessarily been done by Exolon Grup. Unless we otherwise agree in writing, all products are solid strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance, and hereby expressly release us from all liability, in ota, contact or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unal baction. Any statement or recommendation not contained with any claim of any patent relative to any material a in use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group