

# Makrolon® Silent Sound BF AR

## Solid polycarbonate sheet 18 mm



I Line  
Innovative

### Your benefits:

- Tested safety according to ZTV-LSW06/EN 14388
- Anti-graffiti Test according to NF F 31-112
- Bird-friendly (according to ONR 191040)
- Tested for up to 250km/h high speed passing trains

Solid **Makrolon® Silent Sound** sheets are clear, polished, UV-stabilized polycarbonate sheets and available as extended UV and Abrasion-resistant AR (anti graffiti like)/ Bird friendly BF version. They offer extreme impact strength that exceeds the physical properties of other products of their class. Makrolon® sheets resist temperatures of -100 to +120 °C, exhibit high optical clarity and have a good fire rating.

**Makrolon® Silent Sound** sheets meet the sound technical requirements for noise reduction and the demands of road and railway safety, stability such as form and ageing stability. **Makrolon® Silent Sound UV** can be bent cold and also manufactured flat. Furthermore **Makrolon® Silent Sound** sheets can be thermoformed, cold-curved and machined with ease.

### Applications:

**Makrolon® Silent Sound** can be used for noise protection barriers on motorways with heavy traffic, dual carriageways and railways. Incapseling of machinery, transfo's and high voltage cables along tracks.

### Vandalism:

The sheets offer protection against involuntary breakage and wilfull destruction. The sheets are virtually unbreakable and do not splinter.

	Test Conditions	Typical values <sup>(1)</sup>	Unit	Standard
<b>PHYSICAL</b>				
Density		1200	kg/m <sup>3</sup>	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	-	ISO 489
<b>MECHANICAL</b>				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Nominal strain at break	50 mm/min	> 50	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m <sup>2</sup>	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm	80P	kJ/m <sup>2</sup>	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	90P	kJ/m <sup>2</sup>	ISO 180-A
<b>THERMAL</b>				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 <sup>4</sup> /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2
<b>ELECTRICAL</b>				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	-	IEC 60250
Relative permittivity	1 MHz	3.0	-	IEC 60250
Dissipation factor	100 Hz	5	10 <sup>-4</sup>	IEC 60250
Dissipation factor	1 MHz	95	10 <sup>-4</sup>	IEC 60250


<sup>(1)</sup> These values are measured on injection molded samples, and are not intended for specification purposes.

# Makrolon® Silent Sound BF AR

## Solid polycarbonate sheet 18 mm



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.



### RESULTS dB [EN ISO 140-3]

Sum of deviation	26.8
Average deviation	1.79
Displacement designated curve	-15
Sound reduction index $R_w$	37

### SPECTRUM ADAPTATION TERMS

	C	$C_{tr}$
100 - 3,150 Hz	-2	-3
100 - 5,000 Hz	-1	-3
50 - 3,150 Hz	-2	-4
50 - 5,000 Hz	-1	-4
$\Delta L_{ARSF}$ (ZTV-LSW 88)		34
$DL_R$ (DIN EN 1793-2)		34 (B3)

### EUROPEAN CERTIFICATES for Makrolon® Silent Sound UV

#### Resistance to brushwood fire according to (\*):

DIN EN 1794-2, Annex A: Class 2  
ZTV-LSW 06, Section 2.5.4

#### Impact of Stones according to:

DIN EN 1794-1, Annex C: Passed

#### Danger of falling debris according to:

DIN EN 1794-2, Annex B: Class 6

#### tested according to „German Guideline for the approval of cladding for sound barriers“ up to 250 km/h

#### Bird Protection according to:

ONR 191040 (Austrian Standards Institutes) : Passed

#### Anti-graffiti like(\*\*)

according to NF F 31-112

(\*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.  
(\*\*) further information can be found in the related Technical Information