

Product data sheet, January 2020

## Makrolon® multi UV 2/6-8

# Multiwall polycarbonate sheet



#### Your benefits:

- high impact strength
- cold-bendable
- ideal for barrel vaults

**Makrolon® multi UV 2/6-8** is a twinwall polycarbonate sheet of 6 mm thickness. It combines high light transmission, thermal insulation and excellent weather resistance. The sheet is lightweight, impact resistant and easy to install.

**Makrolon® multi UV 2/6-8** is ideal for cold-curved barrel vaults. It can also be installed as flat glazing.


- porches, shelters
- covered walkways
- swimming pool covers
- greenhouses
- partition walls
- industrial glazing
- skylights, northlight glazing
- roofina

The manufacturing width of 2,100 mm is particularly suitable for sections that are cut to size across the width.

The sheets are produced with a coextruded UV-protective layer, which is homogeneously fused with the sheet material. This UV-protected side must be installed facing upwards/outwards. It provides **Makrolon® multi UV** with a highly effective protection against weathering, guaranteed for 10 years.

Area weight		1.3 kg/m <sup>2</sup>			
Sheet width		2,100 mm			
Possible delivery lengths		2,000 to 12,000 mm			
Minimum permissible cold-bending radius (1)		900 mm			
Light transmittance τ <sub>D65</sub> (UV-absorbing) – expected values		clear 1099: white 1125: white 1146: bronze 1845: green 1650: blue 1545:	ca. 82 % ca. 24 % ca. 80 % ca. 51 % ca. 58 % ca. 45 %		
Coefficient of thermal expansion $lpha$		0.065 mm/m °0	0		
Possible expansion due to heat and moisture		3 mm/m			
Max. service temperature without load		120°C			
Fire rating <sup>(2)</sup> • Europe	clear 1099, white 114 bronze 1845	6 } B-s1,0	d0 (EN 13501-1)		

<sup>(1)</sup> The cold-bending must be parallel to the ribs of the sheets, never crosswise (risk of buckling).
<sup>(2)</sup> Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards, except for Product rated "B1" in accordance with DIN 4102.







### Makrolon® multi UV 2/6-8

### Multiwall polycarbonate sheet



Exolon Group S-Line, the standard product line, represents a range of certified quality products which offer the reliable solution for most applications.

to these values.


When using Makrolon® multi UV 2/6-8 in roof or wall installations, the forces exerted by snow and wind loads must be absorbed by a suitable substructure. We recommend implementing the support distance indicated in the diagram for the respective loads.

The diagram shows the load-bearing capacity of Makrolon® multi UV 2/6-8 (supported on all sides, rebate depth ≥ 20 mm) with a standard profile on the longitudinal sides. The load-bearing curves enable the user to calculate the actual load-bearing characteristics of the multi-wall sheets in their support con-

If the rebate depth is smaller, the support distances should be reduced in accordance with the relevant load. For wind forces alone, the loads are permitted to be multiplied by 1.1.

#### Load bearing characteristics (determination):

The component resistance (limit state of load-bearing capacity) of Makrolon® multi UV 2/6-8 has been defined in accordance with the European guideline ETAG 010 regarding practical tests. The characteristic values identified were calculated on the longitudinal sides by considering the chucking effect (standard profiles). The results were partially applied to other widths using simplified, conservative models. The loads were applied as uniformly distributed linear loads, i.e. loads such as snow acting perpendicular to the sheet.



kN/m²	1,050 mm width — — — 2,100 mm width —
1.5	
1.25	
1	
0.75	'\
0.5 peo_	
0.25	,
0	1 2 2 4 5 6 7

These values are guide values, evaluated using test reports on

similar products. Adequate safety values, which should be as-

sessed on a case-by-case basis, are to be observed with regard

In general, experience has proven that a safety factor of 1.3 is

adequate with regard to the measured resistance values. This

These specifications do not replace national regulations,

such as building inspectorate approval in Germany (DIBt),

safety factor is included in the load tables and diagram.

Avis Techniques in France, etc.

\* Further information can be obtained on request

Load	kN/m²	0.5	0.75	1.0	1.25	Width in mm
Length or support	m	2.3	1.7	1.3	1	1,050
spacing A	m	1.7	1.4	1.1	0.7	2,100

Exolon Group also produces solid sheets in polycarbonate (Makrolon® GP) and in polyester (Vivak® and Axpet®). For more information, take a look at www.exolongroup.com.



Exolon Group GmbH Rommerskirchener Str. 21 50259 Pulheim

www.exolongroup.com sales@exolongroup.com The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. Properties analysis must at least include testing to determine suitability from a technical assess well as health safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contact or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is nual bot ashall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.