

Exolon® WS - Welding Shield

Solid polycarbonate sheet for arc welding processes



Your benefits:

- certified according to DIN EN ISO 25980 : 2014
- extreme impact strength
- easy to fabricate

Exolon® WS sheets are polycarbonate sheets which comply with requirements for transparent screens in arc welding processes. They protect against the hazardous radiation emitted during arc welding processes and meet the requirements on light transmission, UV-stability and fire resistance specified in EN ISO 25980: 2014. The sheets are available in different colours.

Exolon® WS sheets offer extreme impact strength that exceeds the physical properties of other products of their class. They resist to temperatures of -100 to +120 °C.

Applications:

Exolon® WS can be used in cases where people outside of the welding area need to be protected against the hazardous radiation of arc welding processes.

Typical applications for **Exolon® WS** are shielding of machines, robots or facilities where arc welding is taking place, such as windows in welding cabins or as separation walls between welding robots.

Exolon® WS is not suitable as a welding filter or visor in welding helmets, or for workplaces where the welder has to be protected against the reflection of welding light.

	Test Conditions	Typical values ⁽¹⁾	Unit	Standard
PHYSICAL				
Density		1200	kg/m ³	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	-	ISO 489
MECHANICAL				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Strain at break	50 mm/min	120	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m ²	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm, notched	80P	kJ/m ²	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	70P	kJ/m ²	ISO 180-A
THERMAL				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/mK	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 ⁻⁴ /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2

⁽¹⁾ These values are measured on injection molded samples, and are not intended for specification purposes.

Exolon® WS - Welding Shield

Solid polycarbonate sheet for arc welding processes



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Available sizes:

Exolon® WS sheets are available in thicknesses 3 and 4 mm in the following size:

Size (standard):

1.250 x 2.050 mm

Colours:

Exolon® WS green 658

Exolon® WS bronze 888

Hazard level: as defined in DIN EN ISO 25980 : 2014

	green 658	bronze 888
3 mm	0.60	0.70
4 mm	0.57	0.80



Exolon Group NV
Wakkensesteenweg 47
8700 Tielt

Belgium

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group