

Product data sheet, February 2026

Curvalite®

Solid copolyester sheet



Your benefits:

- thermoformability
- good impact strength
- suitable for food-contact applications
- good fire rating

Solid **Curvalite®** sheets are made of thermoplastic co-polyester (NPG-based PET-G). They offer good impact strength, a good fire rating and are fully recyclable.

Curvalite® GP clear 099 is a clear transparent sheet with high light transmission and gloss. **Curvalite® GP clear 099** is made from resin which can be used for food-contact applications.

Applications:

Fields of application for **Curvalite®** are: P.O.S. (displays, price tag holders, shelf partitions), direction signs, promotional symbols, food containers and trays, partitions.

Curvalite® can be thermoformed at low energy consumption, short production cycles, high degrees of stretching and accurate mold surface reproduction, without predrying. The sheets are easy to screen print, 3D-print and machine.

	Test Conditions	Typical values	Unit	Standard
PHYSICAL Density		1.29	g/cm ³	ISO 1183-1
MECHANICAL Tensile stress at yield Elongation at break Limiting flexural stress Impact strength	Izod, unnotched Izod notched at 23 °C	> 45 > 25 ca. 70 no break ca. 4	MPa % MPa kJ/m ² kJ/m ²	ISO 527-1/-2 ISO 527-1/-2 ISO 178 ISO 180/U ISO 180/A
THERMAL Vicat softening temperature	Method B50	78	°C	ISO 306

These values are measured on injection molded samples, and are not intended for specification purposes.

Curvalite®

Solid copolyester sheet



Exolon Group S-Line, the standard product line, represents a range of certified quality products which offer the reliable solution for most applications.

Light Transmission:

Test method according to DIN EN ISO 13468. The stated thicknesses are not all available as standard. Please ask us for more information. The stated values are typical values only.

Light transmission in %	1	2	3	4	5	6
Curvalite® GP clear 099	88	86	85	84	83	81

(Tolerance +/- 3%)

Available sizes:

Curvalite® GP clear 099 is available in thicknesses of 1 - 6 mm. Our standard size has the dimension: 3,050 x 2,050 mm.

Please contact us, if you need other dimensions.

Thermoforming:

Due to their flow and mold surface reproduction, **Curvalite®** sheets can be thermoformed at low temperatures without pre-drying. Because of its low specific heat capacity **Curvalite®** requires little energy for thermoforming. Tension in formed parts may influence the impact resistance.

Permanent Service Temperature:

The maximum permanent service temperature without load is approx. 65 °C.

Food compatibility

Curvalite® GP clear 099 is made from resin which can be used for food-contact applications.

Fire Rating (*):

Country	Standard	Rating	Thickness	Color
Europe	EN13501-1	B-s1, d0	1-6 mm	clear 099

(*) fire certificates are limited in time, always check if the mentioned certificate is still valid.

Exolon Group also produces multiwall sheets in polycarbonate (Exolon® multi UV), and solid sheets in polycarbonate (Exolon® GP) and in polyester (Vivak®, Axpert® and Inspria®). For more information, take a look at www.exolongroup.com.



Exolon Group NV
Wakkensesteenweg 47
8700 Tielt
Belgium

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Vivak® is a registered trademark of Exolon Group