

Product data sheet, June 2026

Inspria® GP

Solid HT-copolyester sheet



Your benefits:

- extreme impact strength
- suitable for food-contact applications
- high temperature resistance
- high clarity

Solid **Inspria® GP** sheets are made of Eastman Tritan™ copolyester. They are clear transparent and combine high impact strength with excellent thermoforming properties.

Inspria® GP clear 099 is a clear transparent sheet with extremely high light transmission and high gloss. I

Applications:

Ideal fields of application for **Inspria® GP** are: chocolate moulds, food containers and trays, flat and formed machine coverings, refrigerator doors

Inspria® GP can be thermoformed to extreme degrees of stretching and accurate mold surface reproduction. The sheets can withstand temperatures up to 90°C and are easy to machine.

	Test Conditions	Typical values ⁽¹⁾	Unit	Standard
PHYSICAL Density Moisture absorption	24 h immersion 23°C	1.19 0.5	g/cm ³ %	ISO 1183-1 ISO 62
MECHANICAL Tensile stress at yield Tensile strength Elongation at yield Elongation at break Tensile modulus Flexural modulus Impact strength	Izod notched 23 °C	43 58 7 185 1,548 1,495 93	MPa MPa % % MPa MPa kJ/m ²	ISO 527 ISO 527 ISO 527 ISO 527 ISO 527 ISO 178 ISO 180/1A
THERMAL Coeff. of linear thermal expansion		0.09	mm/m K	ASTM D696

(1) These values are measured on injection moulded samples and are not intended for specification purposes

EASTMAN

Inspria® GP is made of Eastman Tritan™

Inspria® GP

Solid HT-copolyester sheet



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

Light Transmission:

Test method according to DIN EN ISO 13468. The stated thicknesses are not all available as standard. Please ask us for more information. The stated values are typical values only.

Light transmission in %	0.6	0.75	1	1.5	2	3	4	5	6	8
Inspria® GP clear 099	90	90	90	90	90	89	89	89	88	87

Available sizes:

Inspria® GP clear 099 is available on request in thicknesses of 0.60 - 8 mm.

Our standard sizes are the dimensions:
1,250 x 2,050 mm.

Thermoforming:

Inspria® GP sheets can be thermoformed at temperatures between 150 and 175°C. The sheets show excellent flow and mold surface reproduction.

Permanent Service Temperature

The maximum permanent service temperature without load is 90°C

Food compatibility

Inspria® GP clear 099 can be used for food-contact applications

Exolon Group also produces multiwall sheets in polycarbonate (Exolon® multi UV), and solid sheets in polycarbonate (Exolon® GP) and in polyester (Vivak®, Curvalite® and Axpel®). For more information, take a look at www.exolongroup.com.



Exolon Group NV
Wakkensesteenweg 47
8700 Tielt
Belgium
www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. The biocompatibility testing referenced above cannot assure the biocompatibility of final or intermediate products made from Exolon Group products or the suitability of such products for their use in a Medical Application, i.e., the test data cannot be used to conclude that any medical devices manufactured from the Exolon Group products meet the necessary requirements of ISO Standard 10993-1. It is the sole responsibility of the manufacturer of final end-use product to conduct all necessary tests (including biocompatibility tests) and inspections and to evaluate the final product under actual end-use requirements. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Inspria® is a registered trademark of Exolon Group. Eastman Tritan™ is a registered trademark of Eastman.