


# Exolon® FR AR

## Fire retardant polycarbonate sheet with abrasion resistance



### Your benefits:

- extreme impact strength
- good abrasion resistance
- UL94-V0 classification
- excellent weathering resistance



**Exolon® FR AR** sheet is a fire retardant and abrasion resistant polycarbonate sheet that offers glasslike hardness coupled with the impact strength of standard polycarbonate. **Exolon® FR AR** sheets have excellent fire rating: they are UL94-V0 rated as of 3 mm thickness. Additionally, **Exolon® FR AR 8099** offers on both surfaces enhanced resistance against yellowing and hazing for an extended service life in high profile architectural glazing.

**Exolon® FR AR** has a 10-years warranty against breakage and 7-years warranty against delamination and weathering.

### Typical applications for Exolon® FR AR sheet include:

- lighting fixtures and electro technical components and guards which have to comply with UL94 requirements and require improved resistance to scratches and abrasion.
- any application where improved fire behaviour in combination with scratch resistance is needed for fire safe solutions

Due to its scratch-resistant coating, **Exolon® FR AR** cannot be formed like other **Exolon®** sheets.

	Test Conditions	Typical values <sup>(1)</sup>	Unit	Standard
<b>PHYSICAL</b>				
Density		1200	kg/m <sup>3</sup>	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	–	ISO 489
<b>MECHANICAL</b>				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Strain at break	50 mm/min	120	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Taber abrasion resistance	Δ haze after 100 cycles (500 g CS 10F) after 500 cycles	1 – 4 4 – 9	% %	ASTM D1044 & ANSI Z26.1
<b>THERMAL</b>				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 <sup>-4</sup> /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2

<sup>(1)</sup> These values are measured on injection molded samples, and are not intended for specification purposes.

# Exolon® FR AR

## Fire retardant polycarbonate sheet with abrasion resistance



Ideas, innovative, intelligent, interesting... Exolon Group i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

### Light Transmission:

Test Method according to DIN 5036.

The stated thicknesses are not all available as standard. Please ask us for more information.

The stated values are typical values only.

Light transmission in %	2	3	4	5	6
Exolon® FR AR clear 8099	88	88	86	85	84

### Available sizes:

**Exolon® FR AR** is available in thicknesses of 2 – 10 mm and in the following sizes; other sizes, colors and sheet thicknesses on request.

### Colors:

Exolon® FR AR clear 8099

### Sizes:

3,000 x 2,000 mm

### Permanent Service Temperature:

The permanent service temperature without load is approx. 120°C.

### Fire Rating (\*):

Country	Standard	Rating	Thickness	Colour
USA	UL 94	V0	≥ 3 mm	clear 8099

(\*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.



Exolon Group NV  
Wakkensesteenweg 47  
8700 Tielt

Belgium

[www.exolongroup.com](http://www.exolongroup.com)  
[sales@exolongroup.com](mailto:sales@exolongroup.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group